

MARIFLEX® PU 40 SL

High-Modulus
Polyurethane
Joint-Sealant /
Self leveling mastic

TECHNICAL DATA SHEET
Date: 17.11.2023- Version 23

Product Description

MARIFLEX® PU 40SL is a self-leveling, solvent-free, permanent elastic, cold applied and cold curing, two-component, high modulus polyurethane elastomer (mastic) used for horizontal chalking and joint-sealing.

Cures by reaction of the two components.

1

Product Information

- Two component, high modulus polyurethane elastomer (mastic) used for horizontal chalking and joint-sealing.

Packaging

- 5+1 pails

Color

- White, Grey **
- Other RAL colors may be supplied on demand.

Shelf Life

- 9 months from date of production

Storage Conditions

- Storage temperature: 5°-30°C. Products should remain in their original, unopened containers, bearing the manufacturers name, product designation, batch number and application precaution labels.

Advantages

- Simple application.
- Self-leveling.
- Quick application for long horizontal joints.
- UV and weathering resistant.
- Resistant to constant movement.
- Resistant to water, heat and frost.
- Maintain its mechanical properties over a temperature span of -30°C to +90°C.
- Provides excellent adhesion to most construction materials.
- Resistant to detergents, oils, fuels and seawater.

■ Uses

MARIFLEX® PU 40 SL is used for:

- Joint sealing of interior horizontal control joints.
- Adhesive for elastic bonding.
- Horizontal crack filling mastic.

■ Consumption

Consumption depends on volume of the joint or crack to be sealed.

■ Certifications



Technical Data*

PROPERTY	RESULTS	TEST METHOD
Composition	Polyurethane resin + hardener	
Mixing ratio	5 : 1 by weight	
Elongation at break	>200%	ISO 8939
Elastic recovery	>70%	ISO 7389
Hardness (shore A scale)	40	DIN 53504, ASTM D 2240
Application Temperature	5°C to 35°C	
Skin formation time	60 min (at 23°C, 50%RH)	
Polymerized thickness after 24h	Up to 50mm (at 23°C, 50%RH)	
Chemical Properties	Good resistance against water, cleaning agents, and accidental spray with oils, hydrocarbons, acidic and basic solutions (10%).	

■ Application

Surface Preparation

The surface needs to be clean, dry and sound, free of oils or any contamination, which may harmfully affect the adhesion of the mastic. Remove all loose material. Concrete surfaces must be dry and stable (at least 28 days). Moisture content should not exceed 5%. Users must check that the mastic is compatible with the surface in terms of adhesiveness, staining and chemical compatibility (test a section first).

Mixing

Stir Component A well before using. MARIFLEX® PU 40SL Component A and Component B should be mixed by low speed mechanical stirrer, according to the stipulated mixing ratio, for about 3-5 min.

ATTENTION: The mixing of the components has to be effected very thoroughly, especially on the walls and bottom of the pail until the mixture becomes fully homogeneous.

Making the joint:

size the joint. We recommend a joint width between 10 and 30 mm. The width / depth ratio of the joint should be about 2:1.

Priming

Prime absorbent surfaces, like concrete, screed and wood with MARISEAL® 710 primer. Prime non-absorbent surfaces like metal and ceramic tiles with MARISEAL® AQUA PRIMER.

Sealing

Apply the MARIFLEX® PU 40SL mixture (A+B) mastic by pouring into prepared joint / crack. When applying avoid air entrapment. Smooth with joint nail or putty knife. For a better finish, use protection strips.

May be painted after polymerization is complete. Use acrylic or vinyl dispersion paints after testing a section.

■ Safety measures

MARIFLEX® PU 40SL contains isocyanates. See information supplied by the manufacturer. Please study the Safety Data sheet. PROFESSIONAL USE ONLY.

Our technical advice for use, whether verbal or written, is given in good faith and reflect the current level of knowledge and experience with our products. When using our products, a detailed object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We may guarantee only that our products are compliant with their technical specification; correct application of our products therefore falls entirely within your scope of liability and Users are responsible, in any case, for complying with local legislation and for obtaining any required approvals or authorizations, when necessary, either for their purchase and/or for their use. Values in this technical data sheet are given as examples and may not be regarded as specifications. For product specifications contact our technical department. The new edition of the technical data sheet supersedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practice.

* All values represent typical values and are not part of the product specification. **: The applied sealant might yellow and/or fade upon UV exposure.

MARIS POLYMERS S.M.S.A.

Industrial Area of Inofita • 320 11 Inofita • Greece Tel: +30 22620 32918-9
marispolymers@saint-gobain.com • www.marispolymers.com