

MARISEAL® 450

Aliphatic Polyurethane UV-stable Waterproofing Membrane

TECHNICAL DATA SHEET
Date: 15.05.2024

Product Description

MARISEAL® 450 is a premium, liquid-applied, flexible, cold applied and cold curing, polyurethane membrane, used for long-lasting waterproofing. It offers exceptional UV stability and resistance to mechanical exposure.

Based on pure elastomeric hydrophobic aliphatic polyurethane resins, which result in excellent mechanical, chemical, thermal, UV and natural element resistance properties.

Product Information

- One-component, ground & air moisture-cured, cold applied and cold curing, solvent based, aliphatic polyurethane

Packaging

- 7/17 kg metal pails

Color

- Light Grey & Silver Grey

Shelf Life

- 9 months from date of production

Storage Conditions

- Pails should be stored in dry and cool rooms. Protect the material against moisture and direct sunlight. Storage temperature: 5°-35°C. Products should remain in their original, unopened containers, bearing the manufacturers name, product designation, batch number and application precaution labels

Advantages

- Simple application (roller or airless spray)
- When applied forms seamless membrane without joints
- Resistant to water
- Blister free membrane and fast curing even at thick layer
- Resistant to frost
- Provides water vapor permeability, so the surface can breathe
- Provides excellent thermal resistance, it never turns soft.
- Provides excellent weather and UV resistance
- Maintains its mechanical properties over a temperature span of -30°C to +90°C
- The waterproofed surface can be used for light pedestrian traffic
- Resistant to detergents, oils, seawater and domestic chemicals
- Even if the membrane gets mechanically damaged, it can be easily repaired locally within minutes

■ Uses

- Waterproofing of Balconies, Terraces and Verandas
- Protection of Polyurethane High Density Foam Insulation (in case of pedestrian use only with MARISEAL® FABRIC)
- Waterproofing and protection of Concrete constructions

■ Consumption

- 1,4 – 2,5 kg/m² in two or three layers
- This coverage is based on EN 1504 for application by roller onto a smooth surface in optimum conditions. Factors like surface porosity, temperature and application method can alter consumption. In case of MARISEAL® FABRIC reinforcement, consumption increases.

■ Certifications



EN 13813: Screed material and floor screeds (Synthetic resin screed): 1,4 kg/m²



EN 1504-2: Surface protection systems for concrete (Coating): 1,4 kg/m²



Technical Data*

PROPERTY	RESULTS	TEST METHOD
Elongation at Break	150%	ASTM D 412
Tensile Strength	> 15 N/mm ²	ASTM D 412
Water Vapor Permeability	> 5,6 gr/(m ² ·day)	EN ISO 7783:2012
Carbon Dioxide Permeability	0,605 gr/(m ² ·day)	EN 1062-6:2003
Adhesion to concrete	> 2,5 N/mm ² (concrete surface failure)	EN 1542:2001
Hardness (Shore A Scale)	> 85	ASTM D 2240-15
Service Temperature	-30°C to +90°C	Inhouse Lab
Shock Temperature (20min)	200°C	Inhouse Lab
Rain Stability Time	3-4 hours	Conditions: 20°C, 50% RH
Light Pedestrian Traffic Time	18-24 hours	Conditions: 20°C, 50% RH
Final Curing time	7 days	Conditions: 20°C, 50% RH
Chemical Properties	Good resistance against acidic and alkali solutions (5%), detergents, seawater and oils.	



EPD verified



■ Application

Surface Preparation

Careful surface preparation is essential for optimum finish and durability.

The surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the membrane. Maximum moisture content should not exceed 5%. Substrate compressive strength should be at least 25 MPa, cohesive bond strength at least 1,5 MPa. New concrete structures need to dry for at least 28 days. Old, loose coatings, dirt, fats, oils, organic substances and dust need to be removed by a grinding machine. Possible surface irregularities need to be smoothed. Any loose surface pieces and grinding dust need to be thoroughly removed.

WARNING: Do not wash surface with water!

Repair of cracks and joints:

The careful sealing of existing cracks and joints before the application is extremely important for long lasting waterproofing results.

- Clean concrete cracks and hairline cracks, of dust, residue or other contamination. Prime locally with MARISEAL® 710 primer and allow 2-3 hours to dry. Fill all prepared cracks with MARIFLEX® PU 30 sealant. Then apply a layer of MARISEAL® 450, 200 mm wide centered over all cracks and while wet, cover with a correct cut stripe of MARISEAL® FABRIC. Press it to soak. Then saturate MARISEAL® FABRIC with enough MARISEAL® 450, until it is fully covered. Allow 12 hours to cure.
- Clean concrete expansion joints and control joints of dust, residue or other contamination. Widen and deepen joints (cut open) if necessary. The prepared movement joint should have a depth of 10-15 mm. The width:depth ratio of the movement joint should be at a rate of approx. 2:1.

Apply some MARIFLEX® PU 30 joint-sealant on the bottom of the joint only. Then with a brush, apply a stripe layer of MARISEAL® 450, 200 mm wide centered over and inside the joint. Place MARISEAL® FABRIC over the wet coating and with a suitable tool, press it deep inside the joint, until it is soaked and the joint is fully covered from the inside. Then fully saturate the fabric with enough MARISEAL® 450. Then place a polyethylene cord of the correct dimensions inside the joint and press it deep inside onto the saturated fabric. Fill the remaining free space of the joint with MARIFLEX® PU 30 sealant. Do not cover. Allow 12-18 hours to cure.

Priming

Prime very absorbent surfaces like concrete, cement screed or wood with MARISEAL® 710 or with MARISEAL® AQUA PRIMER. Prime non-absorbent surfaces like metal, ceramic tiles and old coatings with MARISEAL® AQUA PRIMER or with MARISEAL® 750. Allow the primer to cure according to its technical instructions.

Waterproofing membrane

Stir well before using. Pour MARISEAL® 450 onto the prepared/primed surface and lay it out by roller, brush or squeegee, until all surface is covered. You can use airless spray allowing a considerable saving of manpower.

ATTENTION: Reinforce always with MARISEAL® FABRIC at problem areas, like wall-floor connections, 90° angles, chimneys, pipes, waterspouts (siphon), etc.

In order to do that, apply on still wet MARISEAL® 450 a correct cut piece of MARISEAL® FABRIC, press it to soak, and saturate again with enough MARISEAL® 450. For detailed application instructions with MARISEAL® FABRIC, contact our technical department. We recommend reinforcement of the entire surface, with MARISEAL® FABRIC. Use 5-10 cm stripe overlapping. After 12-18 hours (not later than 48 hours) apply another layer of MARISEAL® 450.

For demanding applications, apply a third layer of MARISEAL® 450.

ATTENTION: Do not leave MARISEAL® 450 pail open for more than 45 min as it may dry on the surface and on the walls of the pail.

ATTENTION: Do not apply MARISEAL® 450 over 0,6 mm thickness (dry film) per layer. For best results, the temperature during application and cure should be between 5°C and 35°C. Low temperature retards cure while high temperature speeds up curing. High humidity may affect the final finish.

WARNING: MARISEAL® 450 is slippery when wet. In order to avoid slipperiness, sprinkle suitable aggregates onto the still wet coating, to create an anti-slip surface.

Safety measures

MARISEAL® 450 contains isocyanates. See information supplied by the manufacturer. Please study the Safety Data Sheet.

PROFESSIONAL USE ONLY

Our technical advice for use, whether verbal or written, is given in good faith and reflect the current level of knowledge and experience with our products. When using our products, a detailed object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We may guarantee only that our products are compliant with their technical specification; correct application of our products therefore falls entirely within your scope of liability and Users are responsible, in any case, for complying with local legislation and for obtaining any required approvals or authorizations, when necessary, either for their purchase and/or for their use. Values in this technical data sheet are given as examples and may not be regarded as specifications. For product specifications contact our technical department. The new edition of the technical data sheet supersedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practice.

MARIS POLYMERS S.M.S.A.

Industrial Area of Inofita • 320 11 Inofita • Greece Tel: +30 22620 32918-9
marispolymers@saint-gobain.com • www.marispolymers.com