

MARISEAL® 7350

Acrylic Solvent-based Transparent, Glossy UV-stable Coating

TECHNICAL DATA SHEET
Date: 24.10.2023 - Version 23

Product Description

MARISEAL® 7350 is a premium, transparent, glossy, semi-rigid, coating with impact and abrasion strength and very good UV stability, used for as a transparent coating for natural stone sealing or as a transparent concrete sealer

1

Product Information

- One component, glossy, semi-rigid,

Packaging

- 17/4 kg metal pails

Color

- Transparent

Shelf Life

- 18 months from date of production

Storage Conditions

- Pails should be stored in dry and cool rooms. Protect the material against moisture and direct sunlight. Storage temperature: 5°-35°C. Products should remain in their original, unopened containers, bearing the manufacturers name, product designation, batch number and application precaution labels

Advantages

- Simple application (roller or airless spray)
- Resistant to constant, medium abrasion
- Non-yellowing, UV stable
- Gives a glossy and easy-to-clean surface
- No chalking effect
- Resistant to stagnating water and frost
- Maintains its mechanical properties over a temperature span of -20°C to +90°C
- The waterproofed surface can be walked on (pedestrian traffic).
- Resistant to bacteria and fungus
- Stops the creation of dust
- Decorate the surface and improves the working environment

■ Uses

MARISEAL® 7350 is mainly used in floor coating applications, either as a transparent, UV stable, solvent based coating for natural stones or as a transparent concrete sealer.

- Natural Stones
- Concrete
- Power Floated Concrete
- Stamped Concrete, etc.

■ Consumption

- 0,300-0,400 kg/m² in two layers

This coverage is based on practical application onto a smooth surface in optimum conditions. Factors like surface porosity, temperature, humidity, application method and finish required can alter consumption.

■ Certifications



EN1504-2: Surface protection for concrete 0.3kg/m²

PROPERTY	PERFORMANCE
Water vapor permeability:	Class I: sD < 5 m
Capillary absorption and permeability to water:	$\omega < 0,1 \text{ kg/m}^2 \cdot \text{h}^{0,5}$
Adhesion strength by pull-off tests:	$\geq 1,5 \text{ (1,0) 1) N/mm}^2$
Abrasion Resistance	140mg weight loss
Impact Resistance	Class I $\geq 4 \text{ Nm}$
Resistance to thermal shock (70°C)	$\geq 1,5 \text{ (1,0) N/mm}^2$



Technical Data*

PROPERTY	RESULTS	TEST METHOD
Composition	Solvent based Acrylic	
Resistance to Water Pressure	No Leak	DIN EN 1928
Adhesion to concrete	$>1,5 \text{ N/mm}^2$ (concrete failure)	EN 1542
Surface chalking after 2000h of accelerated aging (DIN EN ISO 4892-3, 400 MJ/m ²)	No chalking observed. Chalking grade 0	DIN EN ISO 4628-6
Hardness (Shore D Scale)	20	ASTM D 2240 (15")
UV accelerated ageing, In the presence of moisture	Passed - No significant changes	EOTA TR-010
Service Temperature	-20°C to +90°C	Inhouse Lab
Application Temperature	5°C to 35°C	Conditions: 20°C, 50% RH
Tack Free Time	1-4 hours	Conditions: 20°C, 50% RH
Light Trafficking	12 hours	Conditions: 20°C, 50% RH
Final Curing time	7 days	Conditions: 20°C, 50% RH



EPD verified

■ Application

Application as Transparent Natural Stone Sealer

Surface Preparation

Careful surface preparation is essential for optimum finish and durability. The surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the coating. Maximum moisture content should not exceed 5%. Possible surface irregularities need to be smoothened. Any loose surface pieces and dust need to be thoroughly removed.

WARNING: Do not wash surface with water!

Natural Stone Sealer

Apply MARISEAL® 7350 onto the previously prepared Natural Stone surface by roller in one or two layers.

Application as Concrete Sealer

Surface Preparation

Careful surface preparation is essential for optimum finish and durability.

The surface needs to be grinded with a stone- or a diamond-grinding machine. The surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the coating. Maximum moisture content should not exceed 5%. Substrate compressive strength should be at least 25MPa, cohesive bond strength at least 1.5MPa. New concrete structures need to dry for at least 28 days. Old coatings, dirt, fats, oils, organic substances and dust need to be removed by a grinding machine. Possible surface irregularities need to be smoothened. Any loose surface pieces and grinding dust need to be thoroughly removed.

WARNING: Do not wash surface with water! Do not use a metal-ball blasting machine to grind the surface, because the heavy metal-ball impacts destroy the cohesion of the concrete surface and lower its stability.

Repair of cracks:

Clean cracks and hairline cracks, of dust, residue or other contamination. Fill all cracks with suitable putty. The next day smoothen the putty surface with a sandpaper or a mechanical grinder.

Concrete Sealing:

Make sure that the concrete surface to be coated was previously prepared (grinded and cleaned) and is according to specifications.

Apply MARISEAL® 7350 by roller. After 2-4 hours (not later than 6 hours) apply the second layer.

For best results, the temperature during application and cure should be between 5°C and 35°C. Low temperature retards cure while high temperature speeds up curing. High humidity may affect the final finish.

WARNING: MARISEAL® 7350 is slippery when wet. In order to avoid slipperiness, sprinkle suitable aggregates onto the still wet coating to create an anti-slip surface. Please contact our technical Dept. for more details.

■ Safety measures

MARISEAL® 7350 contains solvents. See information supplied by the manufacturer. Please study the Safety Data Sheet. PROFESSIONAL USE ONLY

Our technical advice for use, whether verbal or written, is given in good faith and reflect the current level of knowledge and experience with our products. When using our products, a detailed object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We may guarantee only that our products are compliant with their technical specification; correct application of our products therefore falls entirely within your scope of liability and Users are responsible, in any case, for complying with local legislation and for obtaining any required approvals or authorizations, when necessary, either for their purchase and/or for their use. Values in this technical data sheet are given as examples and may not be regarded as specifications. For product specifications contact our technical department. The new edition of the technical data sheet supersedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practice.

* All values represent typical values and are not part of the product specification.

MARIS POLYMERS S.M.S.A.

Industrial Area of Inofita • 320 11 Inofita • Greece Tel: +30 22620 32918-9
marispolymers@saint-gobain.com • www.marispolymers.com